

REMARKS


The specification has been amended to correct errors of a typographical and grammatical nature. Due to the large number of corrections thereto, applicants submit herewith a Substitute Specification, along with a marked-up copy of the original specification for the Examiner's convenience. Applicants submit that the substitute specification includes no new matter. Therefore, entry of the Substitute Specification is respectfully requested.

The abstract and claims have also been amended to correct errors of a typographical and grammatical nature.

Entry of the preliminary amendments and examination of the application is respectfully requested.

To the extent necessary, applicant's petition for an extension of time under 37 CFR 1.136. Please charge any shortage in the fees due in connection with the filing of this paper, including extension of time fees, to Deposit Account No. 01-2135 (501.43190X00) and please credit any excess fees to such deposit account.

Respectfully submitted,



Paul J. Skwierawski
Registration No. 32,173
ANTONELLI, TERRY, STOUT & KRAUS, LLP

PJS/MK/DRA/cee
Attachments
(703) 312-6600

MARKED UP VERSION OF ORIGINAL SPECIFICATION

DISPLAY DEVICE

BACKGROUND OF THE INVENTION

~~1. Field of the Invention:~~

5 The present invention relates to an active matrix type display device;
and, more particularly, the invention relates to a display device which includes
pixels constituted of light emitting elements, such as EL (electroluminescence)
elements, which emit light by ~~flowing~~ causing an electric current to flow to light
emitting layers, such as organic semiconductor films, LED (light emitting diode)
10 elements or the like, and pixel circuits which control ~~an~~ the light emitting
operation of these pixels.

~~2. Description of the Related Art:~~

 Recently, along with ~~an~~ the advent of ~~the~~ a sophisticated information
society, the demand for personal computers, a car navigation system, a PDA,
15 information communication equipment and composite products thereof ~~is~~ has
been increasing. As display means for these products, a display device which
is thin and light ~~weighted~~ weight and which exhibits a small power consumption is
most suitable, and a liquid crystal display device or a self-luminous display
device which uses electro-optical elements, such as EL elements or LEDs, ~~is~~
20 has been used as such a display device. __—

———The A display device which uses ~~the latter~~ self-luminous electro-optical
elements has favorable characteristics, such as ~~the~~ a favorable visibility, ~~the~~ a
wide viewing angle characteristic and ~~the~~ a rapid response suitable for display of
moving images, whereby it is considered that such a display device is
25 particularly suitable for image display.

Particularly, with respect to ~~the~~ a display device which uses organic EL elements (also referred to as an organic LED element: hereinafter also abbreviated as OLED in some cases) which ~~utilizes~~ utilize an organic material, such as ~~an organic semiconductor~~ semiconductor material, as light emitting layers, along with the rapid enhancement of the light emitting efficiency and the advancement of the network technology, which enables the video communication, the expectation for ~~the~~ a display device which uses ~~the~~ OLED light emitting elements is high. ~~The~~ An OLED light emitting element has ~~the~~ a diode structure which sandwiches an organic light emitting layer ~~with~~ between two sheets of electrodes.

To enhance the power efficiency of ~~the~~ an OLED display device which is constituted of ~~these~~ OLED light emitting elements, as will be explained later, active matrix driving, which uses thin film transistors (hereinafter also referred to as a TFT) as switching elements of the pixels, is effective.

———Techniques which drive the OLED display device using ~~the~~ an active matrix structure are described in, for example, Japanese Unexamined Patent Publication 1992-328791, Japanese Unexamined Patent Publication 1996-241048, and US Patent Specification 5550066 ~~and the like~~. Further, the drive voltages which are used in the to implement these techniques are referred to in International Patent Publication WO98/36407.

The display device which uses ~~the~~ OLED light emitting elements is ~~configured such that to~~ consists of a first substrate on which forms there is formed a matrix of pixel circuits, each consisting of a switching element and an OLED light emitting element, on a main surface thereof, a second substrate laminated with the first substrate and which protects the OLED light emitting elements which are formed on the main surface of the first substrate ~~is laminated~~, and a seal material, which is applied to the peripheries of both substrates and is

cured so as to isolate and seal the inside of the laminated structure from the outside. Here, for mainly suppressing the deterioration of the OLED light emitting elements caused by moisture, a moisture absorbent member is usually mounted on an inner surface of the second substrate (surface which faces the main surface of the first substrate in an opposed manner). This moisture absorbent member is mounted ~~such that in~~ a recessed portion that is formed in the inner surface of the second substrate, and the moisture absorbent member is adhered to the recessed portion using an adhesive agent, or the moisture absorbent material is applied to a bottom surface of the recessed portion by coating.

The aforementioned patent gazettes and the other documents ~~the inventors of~~ relevant to the present patent application ~~referred~~ are listed as follows.

Patent Document 1: Japanese Unexamined Patent Publication 1992-328791

Patent Document 2: Japanese Unexamined Patent Publication 1996-241048

Patent Document 3: US Patent Specification 5550066

Patent Document 4: International Patent Publication WO98/36407

Patent Document 5: Japanese Unexamined Patent Publication 2000-36381

Patent Document 6: Japanese Unexamined Patent Publication 1997-148066

SUMMARY OF THE INVENTION

The first substrate of a display device includes a display area formed of a pixel circuit in which a large number of pixels are arranged in a matrix array, ~~the~~. The first substrate includes a first seal area at a ~~the~~ periphery thereof outside the display area, and the second substrate includes a second seal area which covers the main surface constituting an inner surface of the first substrate at an area which faces the first seal area of the first substrate. Then, the first

seal area and the second seal area are laminated to each other by way of the ~~a~~
seal material₁ and ultraviolet rays are irradiated from the second substrate side
to cure the seal material₁ thus completing sealing.

In the recent development of an OLED display device, there ~~a method~~
5 has been proposed ~~a method~~ in which a drive circuit area₁ which constitutes
drive circuits for driving the pixel circuits₁ is provided outside the display area₁
which is formed on the main surface of the first substrate₁ and inside the first
seal area, and the drive circuits are arranged in the inside area sealed by the
first substrate and the second substrate. In such a method, the drive circuits
10 can be simultaneously formed with the pixel circuits and the drive circuits ~~are~~
~~incorporated~~₁ and₁ hence, it is possible to obtain an advantage in that an
operation to exteriorly mount the drive circuits can be omitted₁ and the
constitution of the whole display device can be simplified.

However, in curing the seal material which laminates the first substrate
15 and the second substrate together by irradiating ultraviolet rays to the seal
material, there exists the possibility that the ultraviolet rays to be irradiated will
wrap around the drive circuit area and the display area and deteriorate the
characteristics of the drive circuits and the semiconductor films which constitute
the pixel circuits in the display area. Accordingly, in performing curing of the
20 seal material by the irradiation of ultraviolet rays, it is necessary to prevent
wrapping-around of the ultraviolet rays around the drive circuit area and the
display area.

As a countermeasure to cope with this ~~task~~ problem, the use of the ~~a~~
light shielding mask₁ which is used in the manufacture of semiconductor
25 elements₁ has been considered conventionally. ~~The light shielding mask~~
~~performs, as~~ As will be explained later as a comparison example ~~in the~~ with an
exemplary embodiment, ~~the~~ such curing treatment of the seal material is

performed by using a quartz mask which constitutes a light shielding film on portions which are to be blocked from the irradiation of ultraviolet rays₁ and the quartz mask is tightly adhered to the second substrate. However, in using such a method, since there ~~exists~~ is a distance between the drive circuits, the pixel
5 circuits and the quartz mask and hence, the wrapping-around of the ultraviolet rays into the inside of the light shielding film formed on the quartz mask is increased. Accordingly, it is necessary to form the drive circuits such that the drive circuits are arranged close to the display area side. However, this brings about a narrowing of the area of the display area.

10 As another ~~prior arts~~ examples, in Japanese Unexamined Patent Publication 2000-36381 and Japanese Unexamined Patent Publication 1997-148066, propose a technique in which cathode films which constitute OLED elements in a display area are formed of a light shielding metal. This structure, however, ~~has no intention of performing~~ is not intended to perform light
15 shielding of drive circuits in a display device which includes ~~the~~ a structure in which ~~providing the drive circuits~~ are provided inside a ~~seal~~ sealed area.

It is an object of the present invention to provide a display device which has ~~the~~ a structure in which a drive circuit area is provided inside ~~seal~~ a sealed area ~~which laminates between~~ a first substrate and a second substrate ~~that are~~
20 laminated together and which can obviate in a simple structure ~~the deterioration of the~~ characteristics of a display area (a plurality of pixels each having an active element being arranged) and the drive circuit area₁ which may be caused by the irradiation of ultraviolet rays₁ without using a special device for light shielding.

To achieve the above-mentioned object, the present invention is
25 characterized in that ~~to arrange~~ light shielding means is arranged close to the display area where pixel circuits to be blocked from light are formed and the drive circuit area where the drive circuit is formed, and respective types of

constitutional layers provided to the display device also function as the light shielding means. The present invention particularly adopts ~~the~~a structure in which cathode films which constitute OLED elements of the display area on the first substrate also shield the drive circuit area. Further, layers or films made of
5 a moisture absorbent material which are provided to the second substrate are used as light shielding means, or a light shielding film which covers the display area or the drive circuit area is formed over an inner surface or an outer surface of the second substrate.

Due to such structures, a projected image of the light shielding film or
10 the light shielding layer, as viewed from the ultraviolet ray irradiation side, covers the drive circuit area beyond the display area, and hence, the ultraviolet rays are irradiated only to a seal material in the seal area, without using a special light shielding device in the manufacturing steps, whereby it is possible to prevent the deterioration of the characteristics of the organic light emitting layers and
15 semiconductor films which constitute the pixel circuits and the semiconductor films which constitute the drive circuit, thus providing ~~the~~a display device of high quality.

A display device according to a first example of the present invention comprises:

- 20 (a) a first substrate having a display area in which a plurality of pixels are arranged in a matrix ~~manner~~array on a main surface of the first substrate, and a first seal area formed at a periphery of the display area on the main surface of the first substrate, each of the plurality of pixels has a light emitting element and a pixel circuit including an active element; and
25 (b) a second substrate disposed to cover the main surface of the first substrate with a main surface of the second substrate, and having a second seal area at a part of the main surface of the second substrate opposite to the first

seal area of the first substrate, the first substrate and the second substrate are ~~being~~ stuck to each other by a seal material interposed between the first seal area and the second seal area, wherein

(1) the first substrate has a cathode film which is commonly utilized for the
5 respective light emitting elements of the plurality of pixels and covers the second substrate side of the display area,

(2) at least one driving circuit for driving the plurality of pixels is arranged outside of the display area on the main surface of the first substrate,

(3) the second substrate has a recessed portion formed at a part of the
10 main surface of the second substrate within the second seal area and a moisture absorbent layer adhering to the recessed portion, and

(4) the cathode film has a light shielding property and is formed beyond the display area to cover ~~the~~ said at least one driving circuit also.

In the display device according to the first example, the cathode film may
15 be formed as a single layer of a conductive film, or it may have a laminated structure formed by stacking a plurality of ~~the~~ conductive films. The conductive film is formed of e.g. a material selected from a group consisting of aluminum, chromium, titanium, molybdenum, tungsten, hafnium, yttrium, copper, silver, and an alloy which contains at least two elements selected from a group consisting of
20 aluminum, chromium, titanium, molybdenum, tungsten, hafnium, yttrium, copper, and silver. Moreover, the cathode film should be thick enough to cut off ultraviolet rays with which the seal material is irradiated so as to be cured-
thereby.

On the other hand, the light emitting element may be formed of an
25 organic semiconductor material, or it may have a light emitting layer formed of an organic electroluminescent material.

Furthermore, in the aforementioned display device according to the first

example, an area where the at least one driving circuit is provided does not ~~extended-extend~~ outside of the first seal ~~region-area~~ on the main surface of the first substrate, ~~for instance~~. The first seal ~~region-area~~ may be formed to surround the display region disposed in the main surface of the first substrate.

- 5 The second seal ~~region-area~~ may be formed to surround the recessed portion formed at the main surface of the second substrate in the main surface thereof.

A display device according to a second example of the present invention comprises:

- (a') a first substrate having a display area in which a plurality of pixels are
10 arranged in a matrix ~~manner-array~~ on a main surface of the first substrate, and a first seal area formed at a periphery of the display area on the main surface of the first substrate, each of the plurality of pixels includes a light emitting element and an active element; and
- (b) a second substrate disposed to cover the main surface of the first
15 substrate with a main surface of the second substrate, and having a second seal area at a part of the main surface of the second substrate opposite to the first seal area of the first substrate, the first substrate and the second substrate ~~are-~~ being stuck to each other by a seal material interposed between the first seal area and the second seal area, wherein
- 20 (2) at least one driving circuit for driving the plurality of pixels is arranged outside of the display area on the main surface of the first substrate,
- (3') the second substrate has a recessed portion formed at a part of the main surface of the second substrate within the second seal area and ~~an a~~ a moisture absorbent layer having a light shielding property adheres to the
25 recessed portion, and
- (5') the moisture absorbent layer is arranged to cover the display area and the at least one driving circuit.

In the display device according to the second example, the moisture absorbent layer may be formed of a moisture absorbent material containing pigments dispersed therein. The pigments cut off ultraviolet with which the seal material is irradiated so as to be cured ~~thereby~~, and they are formed e.g. of a material selected from a group consisting of carbon black and titanium black.

On the other hand, the moisture absorbent layer may be formed of a moisture absorbent containing dye mixed therein, also. The dye cuts off ultraviolet rays with which the seal material is irradiated so as to be cured ~~thereby~~.

10 In the display device according to the second example, the moisture absorbent layer may be adhered to the recessed portion of the main surface of the second substrate with an adhesive. The adhesive may contain pigments blocking ultraviolet rays with which the seal material is irradiated so as to be cured ~~thereby~~. The pigments are formed of a material selected from a group
15 consisting of carbon black and titanium black, for instance. The adhesive may also contain a dye mixed therein. The dye blocks ultraviolet rays with which the seal material is irradiated so as to be cured ~~thereby~~.

A display device according to a third example of the present invention comprises:

20 (a') a first substrate having a display area in which a plurality of pixels are arranged in a matrix ~~manner~~ array on a main surface of the first substrate and a first seal area formed at a periphery of the display area on the main surface of the first substrate, each of the plurality of pixels includes a light emitting element and an active element; and

25 (b) a second substrate disposed to cover the main surface of the first substrate with a main surface of the second substrate, and having a second seal area at a part of the main surface of the second substrate opposite to the first

seal area of the first substrate, the first substrate and the second substrate ~~are-~~
being stuck to each other by a seal material interposed between the first seal
area and the second seal area, wherein

(2) at least one driving circuit for driving the plurality of pixels is arranged
5 outside of the display area on the main surface of the first substrate,

(3") the second substrate has a recessed portion formed at a part of the
main surface of the second substrate within the second seal area and a coating
film of an a moisture absorbent layer having a light shielding property is put in
the recessed portion, and

10 (5) the moisture absorbent layer is arranged to cover the display area and
the at least one driving circuit.

A display device according to a fourth example of the present invention
comprises:

(a') a first substrate having a display area in which a plurality of pixels are
15 arranged in a matrix ~~manner~~ array on a main surface of the first substrate, and a
first seal area formed at a periphery of the display area on the main surface of
the first substrate, each of the plurality of pixels includes a light emitting element
and an active element; and

(b) a second substrate disposed to cover the main surface of the first
20 substrate with a main surface of the second substrate, and having a second seal
area at a part of the main surface of the second substrate opposite to the first
seal area of the first substrate, the first substrate and the second substrate ~~are-~~
being stuck to each other by a seal material interposed between the first seal
area and the second seal area, wherein

25 (2) at least one driving circuit for driving the plurality of pixels is arranged
outside of the display area on the main surface of the first substrate,

(6) the second substrate has a recessed portion formed at a part of the

main surface of the second substrate within the second seal area and a light shielding film covering the display area and the at least one driving circuit is put in the recessed portion, and

(7) a moisture absorbent layer adheres on the light shielding film.

5 A display device according to a fifth example of the present invention comprises:

(a') a first substrate having a display area in which a plurality of pixels are arranged in a matrix ~~manner~~array on a main surface of the first substrate, and a first seal area formed at a periphery of the display area on the main surface of
10 the first substrate, each of the plurality of pixels includes a light emitting element and an active element; and

(b) a second substrate disposed to cover the main surface of the first substrate with a main surface of the second substrate, and having a second seal area at a part of the main surface of the second substrate opposite to the first
15 seal area of the first substrate, the first substrate and the second substrate ~~are-~~being stuck to each other by a seal material interposed between the first seal area and the second area, wherein

(2) at least one driving circuit for driving the plurality of pixels is arranged outside of the display area on the main surface of the first substrate,

20 (8) the second substrate has a recessed portion formed at a part of the main surface of the second substrate which is opposite to the main surface of the first substrate and located within the second seal area, a moisture absorbent layer adhering to the recessed portion, and a light shielding film being arranged on another main surface thereof at an opposite side thereof to the main surface
25 of the first substrate and covering the display area and the at least one driving circuit.

A display device according to a sixth example of the present invention

comprises:

(a') a first substrate having a display area in which a plurality of pixels are arranged in a matrix ~~manner~~ array on a main surface of the first substrate and a first seal area formed at a periphery of the display area on the main surface of the first substrate, each of the plurality of pixels includes a light emitting element and an active element; and

(b) a second substrate disposed to cover the main surface of the first substrate with a main surface of the second substrate, and having a second seal area at a part of the main surface of the second substrate opposite to the first seal area of the first substrate, the first substrate and the second substrate are being stuck to each other by a seal material interposed between the first seal area and the second seal area, wherein

(1) the first substrate has a cathode film which is commonly utilized for the respective light emitting elements of the plurality of pixels and covers the second substrate side of the display area,

(2') at least one driving circuit for driving the plurality of pixels is arranged in a portion of the main surface of the first substrate being outside of the display area and extending from a part of the first seal area to an inside of the first seal area,

(3) the second substrate has a recessed portion formed at a part of the main surface of the second substrate within the second seal area and a moisture absorbent layer adhering to the recessed portion, and

(4) the cathode film has a light shielding property and is formed beyond the display area to cover the at least one driving circuit also.

In each of the aforementioned display devices according to the second through sixth examples, the light emitting element may be formed of an organic semiconductor material, or it may have a light emitting layer formed of an

organic electroluminescent material.

Here, it is needless to say that the present invention is not limited to the above-mentioned constitutions and the constitutions of embodiments to be described later, and various modifications are conceivable without departing
5 from the technical concept of the present invention. Other objects and ~~constitutions~~-features of the present invention will become apparent from the description of the embodiments described later hereinafter.

BRIEF DESCRIPTION OF THE DRAWINGS

10 Fig. 1 is a cross-sectional view ~~for schematically explaining~~ showing the constitution of a first embodiment of a display device according to the present invention;

Fig. 2 is a cross-sectional view ~~for schematically explaining~~ showing the constitution of a second embodiment of a display device according to the
15 present invention;

Fig. 3 is a cross-sectional view ~~for schematically explaining~~ showing the constitution of a third embodiment of a display device according to the present invention;

Fig. 4 is a cross-sectional view ~~for schematically explaining~~ showing the
20 constitution of a fourth embodiment of a display device according to the present invention;

Fig. 5 is a cross-sectional view ~~for schematically explaining~~ showing the constitution of a fifth embodiment of a display device according to the present invention;

25 Fig. 6 is a cross-sectional view ~~for schematically explaining~~ showing the constitution of a sixth embodiment of a display device according to the present invention;

Fig. 7 is a schematic cross-sectional view of a conventional ultraviolet-ray exposure device ~~served for explaining an advantageous effect of the present invention;~~

Fig. 8 is ~~an explanatory view of a diagram showing~~ an example of a manufacturing process used in the production of a display device according to the present invention;

Fig. 9 is a process flow chart ~~for explaining~~ representing one example of the manufacturing process shown in Fig. 8;

Fig. 10 is a plan view ~~for schematically explaining~~ showing an example of the arrangement of respective functional parts on a first substrate of a display device according to the present invention;

Fig. 11 is ~~an explanatory view of an example of a schematic circuit constitution diagram~~ of one pixel of the display device shown in Fig. 10; and

Fig. 12 is a cross-sectional view ~~for schematically explaining~~ showing an example of the layer structure in the vicinity of one pixel of a display device using organic light emitting elements to which the present invention is applied.

DETAILED DESCRIPTION

Preferred embodiments of the present invention ~~are~~ will be explained in detail in conjunction with drawings ~~which show the embodiments.~~ In the explanation ~~made~~ provided hereinafter, the organic light emitting layers ~~provided to~~ of light emitting elements which constitute respective pixel circuits are classified into organic light emitting layers which perform a monochromic or color display by emitting light with a luminance which is substantially proportional to a current value and with a color (including white) depending on ~~an~~ the organic material thereof, organic light emitting layers which perform a color display by combining color filters of red, green, blue and the like to organic layers which

emit white light₁ and the like. Here, since the ~~detail~~ details of the mechanism of light emission, coloration and the like ~~is~~ are not directly relevant to the ~~explanation~~ an understanding of the present invention, the ~~an~~ an explanation is ~~thereof will be~~ omitted.

5 Fig. 1 is a cross-sectional view ~~for~~ schematically explaining ~~showing~~ the constitution of a first embodiment of a display device according to the present invention. In the drawing, reference symbol SUB1 indicates a first substrate, reference symbol SUB2 indicates a second substrate, and reference symbol SL indicates a seal material. On an inner surface₁ which constitutes a main
10 surface₁ of the first substrate SUB1, organic light emitting elements formed of organic light emitting layers OLE are formed. In Fig. 1, only the organic light emitting layer OLE and a cathode film CD₁ which is formed as a layer above the organic light emitting layer OLE₁ are shown. The organic light emitting element includes pixel circuits constituted of a plurality of thin film transistors and holding
15 capacitances as active elements for selecting and driving the pixel on the organic light emitting layer OLE for each pixel. A display area AR is formed of a large number of these pixels. ~~Then, outside~~ Outside the display area AR and inside the seal area-SL (an area inside of where a seal area SL1 at the first substrate SUB1 side and a seal area SL2 at the second substrate SUB2 side
20 face each other in an opposed manner), a drive circuit area DR₁ where drive circuits are formed₁ is positioned. Here, the active elements are not limited to ~~the~~ thin film transistors.

The display device includes the display area AR₁ in which ~~arranges~~ the pixel circuits are arranged in a matrix array on the main surface of the first
25 substrate SUB1 and the drive circuit area DR₁ where the drive circuits are formed. The cathode films CD₁ which constitute the pixel circuits₁ are provided ~~to~~ in the display area AR₁ and these cathode films CD are formed₁ ~~such that the~~

~~cathode films CD~~ so as to also cover the drive circuit area DR beyond the display area AR. The second substrate SUB2 is a so-called seal can, wherein a recessed portion ALC is formed in ~~an inner surface of~~ the second substrate SUB2, that is, in a surface of the second substrate SUB2 which faces the main surface of the first substrate SUB1. A moisture absorbent member (desiccant agent) DCT is mounted in the recessed portion by way of an adhesive layer FX.

The seal areas SL1, SL2 are formed on respective peripheries of the first substrate SUB1 and the second substrate SUB2, and the seal material (adhesive agent made of ultraviolet ray curing resin) SL is applied between these seal areas SL1, SL2. The first substrate SUB1 and the second substrate SUB2 are laminated to each other such that the respective main surfaces thereof face each other in an opposed manner, and a the distance between both substrates is adjusted to a given value (so-called gap forming step). At this point of time, the seal material SL is sandwiched between the seal area SL1 of the first substrate SUB1 and the seal area SL2 of the second substrate SUB2 in a state such that the seal material SL is not cured. Subsequently, ultraviolet rays UV are ~~made directed~~ to be incident on the second substrate SUB2 (main surface of the second substrate SUB2 opposite to the first substrate SUB1). The seal material SL is cured upon receiving the irradiation of ultraviolet rays UV which pass through the second substrate SUB2 (peripheral portion which surrounds the recessed portion ALC). Accordingly, the first substrate SUB1 and the second substrate SUB2 are integrally fixed to each other by the cured seal material SL. In the display device (display panel) assembled in this manner, the main surfaces (main surfaces having the seal areas SL1, SL2) of the first substrate SUB1 and the second substrate SUB2 which face each other in an opposed manner are ~~also~~ referred to as inner surfaces, while the main surface of the first substrate SUB1 opposite to the second substrate SUB2 and the main

surface of the second substrate SUB2 opposite to the first substrate SUB1 are also referred to as outer surfaces.

Here, the irradiated ultraviolet rays UV are blocked by the cathode films CD which are formed on the inner surface of the first substrate SUB1 and ~~does~~
5 do not reach the display area AR and the drive circuit area DR. ~~A using The~~
wavelength of the ultraviolet rays UV is usually 300nm to 450nm and the intensity of light is 10 to 200mW/cm². Further, to ensure the light shielding effect of the cathode films CD, it is preferable to set ~~a the~~ thickness of the cathode films CD such that the cathode films CD can sufficiently block light ~~of in~~
10 the above-mentioned wavelength band. For example, when the cathode films CD are formed of aluminum, it is preferable to set the thickness of the cathode film CD to a value equal to or more than 50nm, and it is more preferable to set the thickness of the cathode films CD to a value equal to or more than 200nm. With respect to an aluminum film, the light shielding effect is almost saturated
15 when the film thickness of the cathode film CD is equal to or more than 200nm.

When the cathode films are made of aluminum, by setting the film thickness to a value equal to or more than 200nm, no damage is imparted to the semiconductor films of the organic light emitting layers OLE which constitute the display area AR or to the thin film transistors and the semiconductor films of the
20 thin film transistors which constitute the drive circuit area DR. According to this embodiment, without adding ~~the a~~ particular light shielding means, it is possible to shield the display area AR and the drive circuit area DR of the display device from ~~the~~ ultraviolet rays₁ and₁ hence, it is possible to maintain a given
~~performances performance~~ (voltage/current characteristics) for a long period₁
25 and, at the same time, it is possible to obtain ~~the a~~ display device of high quality at a low cost. That is, without adding any new functions to the existing manufacturing facility and, at the same time, without adding a new forming

process, it is possible to manufacture the display device of the present invention. The cathode films CD may be formed of a metal film made of a material selected from a group consisting of aluminum, chromium, titanium, molybdenum, tungsten, hafnium, yttrium, copper and silver or an alloy film made of a material
5 containing the above-mentioned two or more materials.

Fig. 2 is a cross-sectional view ~~for~~ schematically explaining ~~showing~~ the constitution of a second embodiment of the display device according to the present invention. In the drawing, the same reference symbols ~~equal to~~ as those in Fig. 1 indicate identical functional parts. While the embodiment
10 ~~explained~~ described in conjunction with Fig. 1 performs the light shielding at the first substrate SUB1 side, in this embodiment, the display area AR and the drive circuit area DR provided ~~to~~ on the first substrate SUB1 are shielded from light by a moisture absorbent layer DCTS provided ~~to~~ on the second substrate SUB2. To obviate ~~the any~~ contact between the display area AR and the drive circuit
15 area DR provided ~~to~~ at the inner surface of the first substrate SUB1, ~~a~~ the thickness of the moisture absorbent layer DCTS is usually set to 0.1 to 1.0mm. The moisture absorbent layer DCTS is a sheet-like molded product and is fixed to a bottom portion of the recessed portion ALC of the second substrate SUB2 by means of an adhesive agent FX.

20 Provided that the moisture absorbent layer DCTS is a material which can block ultraviolet rays having a wavelength of 300nm to 450nm, known materials can be used. A material which is produced by blending 1% to 30% by weight of black powder, such as carbon black, or titanium black to a material known as a desiccant (for example, a composition which contains barium oxide,
25 calcium oxide, zeolite and the like as main components) can be used. Here, in this embodiment, although the cathode films CD provided ~~to~~ on the first substrate SUB1 side are formed such that the cathode films CD cover only the

display area AR, it is possible to enhance the light shielding effect by forming the cathode films CD ~~such that the cathode films CD~~ so as to also cover the drive circuit area DR in the same manner as the above-mentioned first embodiment. For example, it is possible to prevent UV rays from leaking through the shielding attributed to pin hole defects when the cathode films CD are made of aluminum, and, at the same time, it is possible to set the thickness of the aluminum cathode films CD to equal to or less than 200nm. According to this embodiment, without adding ~~the~~ a particular light shielding means, it is possible to shield the display area AR and the drive circuit area DR of the display device from the ultraviolet rays, and, hence, it is possible to maintain a given performances-performance (voltage/current characteristics), and, at the same time, it is possible to obtain ~~the~~ a display device of high quality at a low cost.

Fig. 3 is a cross-sectional view ~~for~~ schematically explaining showing the constitution of ~~the~~ a third embodiment of the display device according to the present invention. ~~The~~ A repeated explanation of ~~the~~ constitutions-structural features similar to those ~~constitutions~~ shown in Fig. 1 and Fig. 2 ~~is~~ will be omitted. In this embodiment, as a moisture absorbent member which is ~~loaded~~ mounted in the recessed portion ALC formed in the inner surface of the second substrate SUB2, a moisture absorbent material in a liquid form is applied to the whole surface of the bottom portion of the recessed portion ALC of the second substrate SUB2 and is fixed to the bottom portion by heat treatment, thus forming a moisture absorbent film DCTM. Accordingly, in this embodiment, an adhesive agent for fixing the moisture absorbent film DCTM is unnecessary. As the material of the moisture absorbent film DCTM, it is possible to use a material similar to the material used in the second embodiment, ~~explained~~ which was described in conjunction with Fig. 2. Further, by forming the cathode ~~films~~ film CD ~~such that the cathode films CD~~ so that it also covers the drive circuit area DR

in the same manner as the first embodiment, it is possible to further enhance the light shielding effect. According to this embodiment, without adding ~~the~~ a particular light shielding means, it is possible to shield the display area AR and the drive circuit area DR of the display device from ~~the~~ ultraviolet rays, and, hence, it is possible to maintain a given performances-performance (voltage/current characteristics), and, at the same time, it is possible to obtain ~~the~~ a display device of high quality at a low cost.

Fig. 4 is a cross-sectional view ~~for schematically explaining~~ showing the constitution of ~~the~~ a fourth embodiment of the display device according to the present invention. ~~The~~ A repeated explanation of ~~the constitutions-structural features~~ similar to those ~~constitutions~~ shown in Fig. 1 to Fig. 3 ~~is~~ will be omitted. In this embodiment, a light shielding film SHL1 is formed in the recessed portion ALC formed in the inner surface of the second substrate SUB2, and a moisture absorbent layer DCT is fixed to the light shielding film SHL1 as an upper layer using the adhesive agent FX. The light shielding film SHL1 may be obtained by applying or printing a light-shielding composition in a liquid form (resin which is produced by dispersing black powder made of carbon black, or titanium black or the like into a solvent) to the recessed portion ALC and drying the composition, or it may be obtained by forming a film having a given thickness by vacuum evaporating or sputtering a metal material. Further, an inorganic or organic light shielding composition in a film form may be laminated to the recessed portion ALC. Further, by forming the cathode film CD, such so that ~~the cathode film CD~~ it also covers the drive circuit area DR in the same manner as the first embodiment, it is possible to further enhance the light shielding effect. According to this embodiment, without adding ~~the~~ a particular light shielding means, it is possible to shield the display area AR and the drive circuit area DR of the display device from ~~the~~ ultraviolet rays, and, hence, it is possible to

maintain a given performances-performance (voltage/current characteristics),
and, at the same time, it is possible to obtain the a display device of high quality
at a low cost.

Fig. 5 is a cross-sectional view ~~for~~ schematically explaining showing the
5 constitution of the a fifth embodiment of the display device according to the
present invention. ~~The~~ A repeated explanation of the ~~constitutions~~ structural
features similar to those ~~constitutions~~ shown in Fig. 1 to Fig. 4 is will be omitted.
In this embodiment, a light shielding film SL2, similar to the light shielding film
SL1 ~~explained-described~~ in conjunction with Fig. 4, is formed on the outer
10 surface of the second substrate SUB2. The light shielding film SL2 may be
obtained by applying or printing a light-shielding composition in a liquid form
(resin which is produced by dispersing black powder made of carbon black, or
titanium black or the like into a solvent) to the outer surface of the second
substrate SUB2 and drying the composition, or it may be obtained by forming a
15 film having a given thickness by vacuum evaporating or sputtering a metal
material. Further, an inorganic or organic light shielding composition in a film
form may be laminated to the outer surface of the second substrate SUB2.
Further, by forming the cathode films CD ~~such so that the cathode films CD~~ it
also covers the drive circuit area DR in the same manner as the first
20 embodiment, it is possible to further enhance the light shielding effect.
According to this embodiment, without adding the a particular light shielding
means, it is possible to shield the display area AR and the drive circuit area DR
of the display device from the ultraviolet rays, and, hence, it is possible to
maintain a given performances-performance (voltage/current characteristics),
25 and, at the same time, it is possible to obtain the a display device of high quality
at a low cost.

Fig. 6 is a cross-sectional view ~~for~~ schematically explaining showing the

constitution of ~~the~~ a sixth embodiment of the display device according to the present invention. ~~The~~ A repeated explanation of ~~the constitutions structural features~~ similar to those ~~constitutions~~ shown in Fig. 1 to Fig. 4 ~~is~~ will be omitted. In this embodiment, the drive circuit area DR₁ which is provided ~~to on~~ on the main surface of the first substrate SUB1₁ is formed ~~such so~~ so that ~~the drive circuit area DR~~ it is overlapped ~~to on~~ on portions of ~~a the~~ a seal area (a seal area where the seal area SL1 of the first substrate SUB1 side and the seal area SL2 of the second substrate SUB2 side face each other). Although the overall constitution of this embodiment is substantially equal ~~to the same as~~ the same as the overall constitution of the first embodiment of the present invention₁, ~~explained as described~~ explained as described in conjunction with Fig. 1, this embodiment differs from the first embodiment ~~with respect to a point in~~ in that the drive circuit area DR is formed at a position where the drive circuit area ~~DR enters~~ extends into the seal area. Since ~~the other constitutions structural features~~ are equal to the constitutions the same as shown in Fig. 1, the a repeated explanation ~~is thereof~~ will be omitted.

According to this embodiment, by forming the drive circuit area DR at the position where the drive circuit area ~~DR enters~~ extends into the seal area, it is also possible to increase the display area AR₁ and, hence, ~~the a~~ a display device having a large screen can be realized using without increasing the size of the substrate ~~having the same size~~. Here, although the constitution of the first substrate SUB1 side is formed in the same manner as the constitution shown in Fig. 1, it also may be formed in the same manner as the constitutions ~~explained described~~ explained described in conjunction with Fig. 2 to Fig. 5. Further, the constitution of the second substrate SUB2 side may be formed in the same manner as the ~~constitution explained~~ constitutions described in conjunction with Fig. 2 to Fig. 5. According to this embodiment, without adding ~~the a~~ a particular light shielding means, it is possible to shield the display area AR and the drive circuit area DR

of the display device from the ultraviolet rays₁ and₁ hence, it is possible to maintain a given performances-performance (voltage/current characteristics)₁ and, at the same time, it is possible to obtain ~~the~~ a display device of high quality at a low cost.

5 ~~Here~~Now, a comparison example is ~~explained with respect to~~ will be described to highlight the features of the present invention. Fig. 7 is a schematic cross-sectional view of a conventional ultraviolet-ray exposure device for explaining the advantageous effects of the present invention.

Conventionally, a light shielding mask MSK₁ which ~~forms~~ includes a light
10 shielding film SHP formed on a quartz glass QG₁ is tightly adhered to an outer surface of ~~a~~ the second substrate SUB2, and ultraviolet rays UV are irradiated to a seal material SL from the second substrate SUB2 side. To prevent leaking of the ultraviolet rays UV incident on one of the main surfaces (lower surface shown in Fig. 7) of the second substrate SUB2 to ~~a~~ the display area AR (active
15 elements of respective pixels arranged inside thereof) and ~~a~~ the drive circuit area DR (drive circuits including active elements) of the first substrate SUB1, the light shielding mask MSK is tightly adhered to one of main surfaces (lower surface shown in Fig. 7 on which the ultraviolet rays UV are incident) of the second substrate SUB2 in accordance with steps to be described hereinafter.

20 First of all, the light shielding mask MSK is placed on a transparent lower suction stage VST2₁ and the second substrate SUB2 is placed on the light shielding mask MSK. A seal material SL, for example, from a dispenser is applied to ~~a~~ the periphery (seal area SL2) of the main surface of the second substrate SUB2. ~~On the other hand~~ Then, the first substrate SUB1 is conveyed
25 by an upper suction stage VST1₁ provided with a vacuum chuck₁ to a position above the second substrate SUB2 in a state ~~that~~ in which the main surface of the first substrate SUB1₁ on which the display area AR and the drive circuit area

DR are formed, faces downwardly. Subsequently, the positions of the upper suction stage VST1 and a lower suction stage VST2 are adjusted horizontally. ~~A-Next, the~~ periphery (seal area SL1) of the main surface of the first substrate SUB1 is brought into contact with the seal material SL that has been applied to the periphery of the main surface of the second substrate SUB2. ~~Further~~Thus, the main surface of the first substrate SUB1 and the main surface of the second substrate SUB2 are laminated to each other with a given distance therebetween. In this state, ultraviolet rays UV₁ incident on the periphery of the second substrate SUB2 from the lower suction stage VST2 side, are irradiated to the seal material SL so as to cure the seal material SL.

However, as described previously, since ~~the-a~~ large distance exists between the area to be blocked from the light and the light shielding mask, it is difficult to ~~obviate-prevent~~ the irradiation of ultraviolet rays to the area to be blocked from the light, ~~which-so that unwanted irradiation~~ is caused by wrapping-around of the ultraviolet rays. Particularly, it is difficult to obviate ~~damages-the damage~~ which may be caused by the wrapping-around of the ultraviolet rays to the drive circuit area adjacent to the seal material SL.

Further, such a ultraviolet-ray exposure device uses ~~the-an~~ expensive quartz mask₁ and, hence, the device is not suitable for the manufacture of ~~the-a~~ display device having a large screen size. Further, since the light shielding mask MSK and the second substrate SUB2 must be held using the same lower suction stage VST2, ~~a-the~~ holding mechanism becomes complicated. Further, ~~the-an~~ alignment of three components, consisting of the first substrate SUB1, the second substrate SUB2 and the light shielding mask MSK₁ becomes necessary, and, hence, ~~there is no way but a~~ it is inevitable that the mechanism for alignment becomes complicated. Further, the light shielding film SHP₁ which is usually formed of a chromium film₁ is brought into contact with the second

substrate SUB2, and, hence, flaws or the like occur on the light shielding film SHP, ~~whereby so that there exists is a limit with respect to~~ the repeated use of the light shielding film SHP. In view of the above, when the ultraviolet-ray exposure device shown in Fig. 7 is used, this ~~pushes up~~ increases the cost of the display device. Accordingly, by adopting the above-mentioned respective embodiments of the present invention, it is possible to shield the display area AR and the drive circuit area DR from the ultraviolet rays without adding any special light shielding means.

Fig. 8 is ~~an explanatory view of a block diagram showing~~ an example of a manufacturing process used in the fabrication of the display device according to the present invention. Fig. 9 is a process flow chart for explaining an example of the manufacturing process shown in Fig. 8. In Fig. 8, glass (first substrate glass) which constitutes a base material of the first substrate and glass (second substrate glass) which constitutes a base material of the second substrate are subjected to cleaning, degassing, cooling and the like, respectively, by a pretreatment facility PPS. Here, a recessed portion in which a moisture absorbent (desiccant) material is mounted is formed in the second substrate glass. Then, the first substrate glass is conveyed to a first vacuum evaporation apparatus V1S and hole injection layers and ~~an~~ organic light emitting layers are formed on output electrodes (or anodes connected to the output electrodes) of the thin film transistors. When the color display is performed with light emitting colors of the organic light emitting layers per se, the formation of organic light emitting layers of three colors consisting of red (R), green (G) and blue (B) is performed sequentially.

The first substrate glass to which the treatment in the first vacuum evaporation apparatus V1S ~~is~~ has been applied is conveyed to a second vacuum evaporation apparatus V2S where the vacuum evaporation or the like of

the cathodes is applied. The first substrate glass ~~to-on~~ which the cathodes are ~~have been~~ deposited ~~are-is~~ conveyed to a sealing apparatus SS. On the other hand, the pretreated second substrate glass is conveyed to the sealing apparatus SS and, thereafter, they are transferred to a desiccant dispenser chamber (moisture absorbent loading chamber) DDS₁ ~~and-where~~ a moisture absorbent is loaded in the recessed portion. The second substrate glass on which the moisture absorbent is loaded is again returned to the sealing apparatus SS and is laminated to the first substrate glass. This lamination is performed such that a seal material made of an ultraviolet ~~rays-ray~~ curing resin is applied between respective seal areas of the first substrate glass and the second substrate glass and the substrate glasses are laminated to each other. Ultraviolet rays are radiated to the seal material from the second substrate glass side to cure the seal material. Here, it may be possible to perform the heat treatment after irradiation of the ultraviolet rays so as to completely cure the seal material.

The laminated product₁ which ~~is-was~~ formed by integrally laminating the first and the second substrate glasses using the seal material and by curing the seal material₁ is taken out from the sealing apparatus SS and is cut into individual display devices. A flexible printed circuit board for signal connection is mounted on the display device, aging treatment is applied to the display device₁ and, thereafter, the display device is incorporated into a ~~necessary~~ housing₁ thus completing the fabrication of the display device.

The above-mentioned manufacturing process ~~is-will be~~ further explained in conjunction with Fig. 9. First of all, on the base-material glass substrate which constitutes the first substrate glass (first substrate glass), the thin film transistor and the semiconductor circuit₁ which functions as the driver circuit for the thin film transistor₁ which constitute the pixel circuit for the organic light

emitting element₁ are formed for every display device. The light emitting layer of the organic light emitting element OLE is formed on the first substrate glass. In forming the OLE light emitting layer, the pretreatments₁ such as cleaning, degassing, cooling and the like₁ are applied to the substrate₁ which includes the thin film transistor circuit formed in the preceding step₁ and, thereafter, the hole injection layer and the organic light emitting layer are applied to each pixel portion of the display area. Finally, the cathode film is formed to obtain the first substrate.

On the other hand, the recessed portion₁ which houses the moisture absorbent material therein₁ is formed in the second substrate glass which constitutes the sealing substrate. The moisture absorbent material is loaded on the second substrate glass after forming the recessed portion₁ and, thereafter, the second substrate glass is laminated to the first substrate glass by applying the seal material. After curing the seal material by the irradiation of ultraviolet rays, the heat treatment is applied as the a post-curing treatment. Thereafter, the laminated product is cut into individual-sized display devices. The flexible printed circuit board for connection with the external circuit is connected to the display device₁ and, thereafter, the display device is incorporated into the housing₁ whereby the display device is completed as a module.

Fig. 10 is a plan view ~~for schematically explaining~~ showing an example of the arrangement of respective functional portions on the first substrate of the display device according to the present invention. The display device shown in Fig. 10 corresponds to the above-mentioned first embodiment of the present invention. On the ~~most-largest~~ portion of at the center of the first substrate SUB1, the display area AR is formed. In this drawing, at both sides, that is, at the left and the right sides of the display area AR, drive circuits (scanning drive circuit) GDR-A and GDR-B are arranged. Gate lines GL-A, GL-B which extend

from the respective scanning drive circuits GDR-A and GDR-B are alternately formed. Further, another drive circuit (data drive circuit) DDR is arranged at the lower side of the display area AR₁ and drain lines DL which constitute data lines are formed such that the drain lines DL intersect the gate lines GL-A, GL-B.

5 Further, a current supply base line CSLB is arranged at the upper side of the display area AR₁ and current supply lines CSL extending from the current supply base line CSLB are formed. In this constitution, one pixel PX is formed in a portion surrounded the area defined by the gate lines GL-A, GL-B, the drain line DL and the current supply line CSL. Then, inside the seal material SL, the
10 cathode films CD are formed such that the cathode films CD covers so as to cover the display area AR, the respective scanning drive circuits GDR-A, GDR-B and the data drive circuit DDR. Here, reference symbol CTH indicates a contact area which is served used for connecting the cathode films to cathode film lines which are formed as a layer below the first substrate.

15 Fig. 11 is an explanatory view of a schematic circuit diagram showing an example of the circuit constitution of one pixel shown in Fig. 10. This example of the circuit constitution The pixel is constituted of a thin film transistor TFT1 for switching, a thin film transistor TFT2 for driving organic light emitting element OLED and a capacitance CPR for holding data. The thin film transistor TFT1
20 has a gate electrode thereof connected to the gate line GL-A, a drain electrode thereof connected to the drain line DL and a source electrode thereof connected to one pole of the capacitance CPR. On the other hand, the thin film transistor TFT2 has a gate electrode thereof connected to the source electrode (one pole of the capacitance CPR) of the thin film transistor TFT1, a drain electrode thereof
25 connected to the current supply line CSL and a source electrode thereof connected to an the anode AD of the organic light emitting element OLED. A cathode CD of the organic light emitting element OLED constitutes the cathode

film ~~explained-described~~ in conjunction with the above-mentioned ~~embodiment~~
embodiments.

Fig. 12 is a cross-sectional view ~~for schematically explaining~~ showing an
example of the layer structure in the vicinity of one pixel of the display device
5 which uses ~~the-an~~ organic light emitting element to which the present invention
is applied. On the main surface of the first substrate SUB1, ~~the-there are~~ thin
film transistors, each of which is constituted of a poly-silicon semiconductor film
PSI, a gate electrode GT (gate line GL), a source or a drain electrode SD
(source electrode in the drawing) ~~are formed~~. Reference ~~symbols-symbol~~ IS
10 (IS1, IS2, IS3) ~~indicate-indicates~~ interlayer insulation layers and PSV indicates a
passivation layer.

The thin film transistor shown in Fig. 12 corresponds to the thin film
transistor TFT2 ~~for driving~~ shown in Fig. 11. The anode AD which constitutes
the organic light emitting element is connected to the source electrode SD, and
15 the light emitting layer OLE is formed on the anode AD. Further, cathode film
CD is formed on the light emitting layer OLE as an upper layer. On the other
hand, on the inner surface of the second substrate SUB2, the moisture
absorbent layer DCT is mounted using an adhesive agent FX for mainly
preventing ~~the-deterioration~~ of the light emitting layer OLE caused by moisture.
20 The present invention displays images with the pixels which are constituted in
the above-mentioned manner.

As has been explained heretofore, according to the present invention, by
providing the light shielding means close to the display area on which the pixel
circuits that are to be blocked from the ultraviolet rays are formed and the drive
25 circuit area where the drive circuits are formed, it is possible to ~~make-cause~~ the
ultraviolet rays to be irradiated to only the seal material in the seal area, without
using ~~the-a~~ special light shielding device in the manufacturing process; and,

hence, it is possible to prevent the deterioration of characteristics of the organic light emitting layer and the semiconductor films which constitute the pixel circuits and the semiconductor films which constitute the drive circuits, whereby ~~the~~a display device of high quality can be obtained.